

**PREH-610 橡胶改性耐酸碱防腐漆****PREH - 610 Rubber Modified Acid and Alkali Proofing****Anticorrosive Coating**

产品特性 Characteristics	具有优异的耐强酸、耐强碱、耐大气老化、耐臭氧层等性能； Excellent resistance to strong acid, strong alkali, atmospheric cracking and ozone layer; 同时具有良好的物理性能，耐化工大气性能。 Good physical property with resistance to chemical atmosphere.	
产品用途 Uses	适用于室外化工设备、钢架、水泥墙面等防腐 An anticorrosive coating for outdoor chemical equipment, steel frame and cement wall, etc.	
颜色 Color	各色 All colors	
施工条件 Application method	无气喷涂 airless spray 喷嘴尺寸 nozzle tip 压力 nozzle pressure 稀释比率 thinning ratio	推荐 recommended 0.5~0.6mm 100~150kg/cm ² 0~10%（重量比）
	适用于无气喷涂、空气喷涂、刷涂及辊涂。 May be applied by airless spray, air spray, brush, or roller.	
稀释剂 Thinner	专用稀释剂 Special thinner	
混合比率 Mixing ratio	单组分 One-pack	
涂装膜厚 Film thickness	干膜: 30μm/道 湿膜: 55μm/道 Dry film thickness :30μm/coat Wet: film thickness :55μm/coat	
固体含量 Solid content	60%	
比重 Specific gravity	1.20	



涂覆率 Spreading rate	理论值 : 0.10kg/m ² /30μm Theoretical: 0.10kg/m ² /30μm	0.083L/m ² /30μm 0.083L/m ² /30μm
实际值 : 与表面处理, 外界环境, 施工方法等多种因素有关。 Practical: varies depending on the surface treatment, environment and application methods.		
干燥时间 Drying time	温度℃ temperature	10 20 30
	指触干燥 mins. dry to touch	20 30 20
	半硬干燥 hrs dry hard	6 5 4
涂装间隔 Coating interval	Min. 最小 (hrs) Min. (hrs) Max. 最大 (hrs) Max. (hrs)	6 5 4
储存期限 Shelf life	一年 12 months	
包装规格 Package	20 公斤/桶 20 kg/barrel	
表面处理	用清水冲去盐分以及其它水溶性污物。 Remove salt and other water-soluble contaminants by fresh water hosing 依照 SSPC-SP1 溶剂清洗标准除去油脂。 Remove oil thoroughly with suitable detergent in accordance with SSPC-SP1 用喷砂方式除去铁锈、氧化皮达到 ISO Sa2.5 级; The rust and scale should be thoroughly cleaned by abrasive blasting to ISO Sa2.5. 用高压空气吹扫除去灰尘等污物; Remove dust and dirt by high-pressure air before paint application 水泥底材应彻底干燥清洁, 无灰尘、污物。 The cement substrate shall be thoroughly dry, clean, and free of dust and dirt.	
适用底材 Compatible substrate	裸钢、水泥构件。 Bare steel and cement components	



安全注意事项 Safety Precautions	<p>任何油漆施工中均应保证提供以下措施:</p> <p>The following shall be guaranteed during any paint applications:</p> <p>避免接触皮肤和眼睛。</p> <p>Avoid skin and eye contact.</p> <p>如果油漆接触到皮肤或眼睛, 应用大量水冲洗并立即就医。</p> <p>In case of skin or eye contact, flush with large amount of water and immediately get medical attention.</p> <p>保证良好的通风。</p> <p>Assure well-ventilated working place.</p> <p>小心火灾或爆炸。</p> <p>Take precautions of the risks of fire or explosion.</p> <p>现场遵守一切健康安全规定。</p> <p>Observe all health and safety regulations on site.</p>
提醒注意 Declaration	<p>本说明书所提供信息均为目前我方所掌握最全面正确的资料, 鉴于产品使用条件非我方所能控制, 此中信息不含担保, 即仅在选取产品上对买方负责。由于我公司产品及生产工艺的不断发展, 此中所有信息均以我方确认为准。</p> <p>The information given on this technical data sheet is correct to the best of our knowledge. In consideration of the application conditions of the product are beyond our control, so no guarantee is involved herein, namely, we are responsible for the buyers only in terms of their selecting a product. All data must be clarified from our company because of the constantly improvement of our product and its manufacturing process.</p>
