



FXGL-3 高氯化聚乙烯防腐面漆

FXGL-3 High Chlorinated Polyethylene Anticorrosive Finish

产品特性 Characteristics	干燥快, 优异的物理机械性能 Fast drying, excellent physical and mechanical properties	
	极好的耐水性和耐腐蚀性 Excellent water and corrosion resistance	
	良好的耐酸碱性 Good acid and alkali resistance	
	极好的耐候性 Excellent weather resistance	
	良好的施工性能 Good workability	
产品用途 Uses	主要用于石油化工建筑、设备、管线、水泥面等受化工大气腐蚀的设施, 亦可用于铁路、桥梁、高压输电线、海上钻探及采油设施, 各种车辆底盘、重型机械。 Mainly used in chemical building facilities, equipment, pipelines, oil and other cement surfaces exposed to chemical atmospheric corrosion, and for railways, bridges, high-voltage power lines, water drilling and oil production facilities, a variety of vehicle chassis and heavy machinery.	
颜色 Color	白色及各色 White and other colors	
施工条件 Equipment	无气喷涂 airless spray 喷嘴尺寸 nozzle orifice 压力 nozzle pressure 稀释比率 thinning ratio 适用于常规的喷涂、刷涂和辊涂	推荐 recommended 0.4~0.5mm 100~150kg/cm ² 0~10% by weight (重量比) May be applied by spray, brush, or roller.
稀释剂 Thinner	专用稀释剂 Special thinner	
混合比率 Mixing ratio	单组分 Single component	
涂装膜厚 Film thickness	干膜: 30μm/道 湿膜: 60μm/道 Dry film thickness: 30μm/coat Wet film thickness: 60μm/coat	
固体含量	55%	



Solid content	55%			
比重 Specific gravity	1.2			
涂覆率 Coverage rate	理论值 : 0.11 千克/平方米/30 μ m Theoretical: 0.11 kg/m ² /30 μ m	0.092L/平方米/30 μ m 0.092L/m ² /30 μ m		
	实际值 : 与表面处理, 外界环境, 施工方法等多种因素有关。 Actual : depending on the surface treatment, environment and application methods.			
干燥时间 Drying time	温度(temperature)	10 $^{\circ}$ C	20 $^{\circ}$ C	30 $^{\circ}$ C
	指触干燥(dry to touch)	40mins	30mins	20mins
	实干(dry to handle)	6hrs	5hrs	4hrs
涂装间隔 Coating interval	Min. 最小 Max. 最大	6hrs —	5hrs —	4hrs —
储存期限 Shelf life	一年 12 months			
包装规格 Packing	单组份包装: 20kg/桶 One component package : 20kg/bucket			
表面处理 Surface preparation	底漆表面应清洁干燥, 无污物 The surface of primer should be clean, dry and free from contamination 注意施工时与底漆的涂装间隔 Please take care of coating interval.			
涂装配套 Coating system	适用下涂: 高氯化聚乙烯底漆、高氯化聚乙烯中间漆或参考我公司配套 Under coating : High Chlorinated Polyethylene Anticorrosive Primer, High Chlorinated Polyethylene Anticorrosive Intermediate Coat, or refer to our coating system.			
安全注意事项 Safety Precautions	任何油漆施工中均应保证提供以下措施: The following shall be guaranteed during any paint applications: 避免接触皮肤和眼睛。 Avoid skin and eye contact. 如果油漆接触到皮肤或眼睛, 应用大量水冲洗并立即就医。 In case of skin or eye contact, flush with large amount of water and immediately get medical attention. 保证良好的通风。			



Assure well-ventilated working place.
小心火灾或爆炸。
Take precautions of the risks of fire or explosion.
现场遵守一切健康安全规定。
Observe all health and safety regulations on site

提醒注意
Declaration

本说明书所提供信息均为目前我方所掌握最全面正确的资料，鉴于产品使用条件非我方所能控制，此中信息不含担保，即仅在选取产品上对买方负责。由于我公司产品及生产工艺的不断发展，此中所有信息均以我方确认为准。

The information given on this technical data sheet is correct to the best of our knowledge. In consideration of the application conditions of the product are beyond our control, so no guarantee is involved herein, namely, we are responsible for the buyers only in terms of their selecting a product. All data must be clarified from our company because of the constantly improvement of our product and its manufacturing process.
